













HXL-120

HXL-140



HXL-207



HXL-208




HXL-212



HXL-334

## LET US HELP YOU ACHEIVE YOUR GOALS

- ① UV coating
- 2 High-density wear layer
- ③ Printing layer
- 4 Fiber-glass layer\*
- (5) Backing layer



Construction: 5.0mm LVT
Wear-layer: 0.5mm wear-layer
Edge: Mini-micro-beveled edge
Size/Packaging: Plank size:1535×226×5mm

2.7753sqm / carton, 8 planks per carton, 27.0kgs/carton

| Properties  | Test Method                           | Unit   | Test Result   |            | Remarks  |
|---|---------------------------------------|--------|---|------------|--|
| <b>Dimensional stability</b> (Expansion or shrinking) | BS EN ISO 23999:2012                  | %      | Manufacturing direction   | 0.06       | Heating temperature:<br>80℃<br>Heating time: 6h  |
|   |                                       |        | Across-manufacturing direction  | 0.03       |  |
| Curling after exposure to heat                        |                                       | mm     | 0   |            | Heating time: on   |
| Peel Resistance<br>(top layer)                        | BS EN ISO<br>24345:2012               | N/50mm | Machine direction   | 80         | Loading rate: 100mm/min  |
|   |                                       |        | Across machine  | 75         |  |
| Residual indentation                                  | EN ISO 24343-1:2012                   | mm     | 0.06  |            | Pass   |
| Staining and resistance to chemicial                  | EN ISO 26987:2012                     | /      | Not affected  |            | Pass   |
| Wear resistance (0.5mm/20mil)                         | EN 660-2:1999<br>+A1:2003 and         | /      | Wear group: T   |            | Pass   |
| Color fastness to light                               | EN649:2011<br>EN ISO 105-B02:2014     | /      | Grade (Bluewood Std) 6  |            | Meets requirement  |
| Effect of a castor chair                              | EN 425:2002                           | /      | No visible damage   |            | Pass   |
| Slip resistance                                       | DIN 51130:2014-02                     | /      | Critical angle of inclination: 12.0   | R10        | Pass   |
| RoHS Directive 2011/65/EU                             | IEC 62321                             |        | Not Detected  |            | Pass   |
| Phthalates (DBP, BBP, DINP, DNOP, DIDP)               | EN14372:2004                          |        | Not Detected  |            | Meets requirement  |
| REACH   | Regulation (EC) No<br>1907/2016 REACH | %      | According to the specified scope and evaluation screening, the test results of SVHC are less than 0.1%(w/w) |            | 169 Substances of Very<br>High Concern(SVHC) for<br>authorization by European<br>Chemicals were Not<br>Detected. |
| Fire-resistant rate                                   | EN ISO 9239-1                         | /      | Critical flux (kW/m2)   | ≥11        | - Pass   |
|   | EN ISO 11925-2<br>Expsure = 15s       | /      | Smoke (%xminutes) Fs ≤ 150 mm   | 160<br>YES | Pass   |
| VOC (Floorscore)                                      | CDPH/EHLB/Standard<br>Method V1.2     | /      | 35 types of chemicals   |            | Pass   |
| IIC - IMPACT INSULATION                               | ASTM E492-09                          | /      | Calculated Impact Insulation Class: IIC 55  |            |  |
| STC-SOUND TRANSMISSION                                | ASTM E90-09                           | /      | Calculated Sound Transmission Class: STC 49   |            |  |